

- Ind. A1*
1. Method for bleaching of cellulose pulp having medium consistency without using high-shear mixers, comprising the introduction into the pulp stream via radially arranged injection devices of a stream of ozone-containing gas generated from pressurized oxygen or a mixture of pressurized oxygen with at least one gas or liquid and having an ozone concentration of at least about 20 % by weight.
- 5
2. A method according to claim 1, wherein the introduction of ozone is carried out at a pressure of at least 10 bar.
- 10
3. A method according to claim 1 or 2, wherein said ozone-containing gas is introduced via at least two nozzles adapted to direct the gas into the pulp stream.
4. A method according to claim 3, wherein said nozzles are adapted to direct the gas in a direction essentially perpendicular to the pulp stream.
- 15
5. A method according to any claim 1-4, wherein following gas injection the pulp stream is fed to a dynamic low to medium intensity mixer.
- 20
6. A method according to any claim 1-5, wherein ozone-carrying gas is introduced by means of porous metal injector members.
- add C2*

09763221.051501

AMENDED SHEET